



Alcatel Singlemode Fiber is designed to provide optimum performance in both the 1310nm and 1550nm wavelength operating ranges, with a low dispersion in the 1310nm operating window. Alcatel's Singlemode Fiber can be used in loose tube, tight buffered and ribbon cable configurations.

Although a common application of Singlemode Fiber is terrestrial long-distance networks, Alcatel's Singlemode Fiber is optimized for Access and Enterprise networks, where high rates of transmission are becoming increasingly more prevalent.

All of Alcatel's fibers are further enhanced with the proprietary Alcatel Fiber Coating (AFC™) process and Colorlock™.

These proprietary processes complement the fiber to provide a complete solution ensuring the highest in performance, reliability and durability, even in the harshest environments. Additionally, Alcatel's fibers are manufactured utilizing the proprietary Advanced Plasma and Vapor Deposition (APVD) process. APVD has been specially developed to ensure the highest quality and purity of all Alcatel fibers.



Singlemode Cabled Fiber is still the most prevalent fiber used in today's fiber optic networks. Alcatel's Singlemode Fiber provides optimum performance in terms of distance, high bit-rates and capacity for a diverse range of applications.

As one of the world's largest manufacturers of communication products, Alcatel has the expertise, technology and manufacturing resources to provide a total end-to-end solution to support your fiber, cable, and systems requirements.

FEATURES	BENEFITS
▶ Keeps attenuation and dispersion low; highly efficient for 1310nm and 1550nm operating ranges	▶ Superior performance ideal for access and enterprise networks
▶ Fully compatible in terms of transmission, connections and installation tools	▶ Open standards for multi-sourcing worldwide
▶ Superior stripping ease, using both mechanical and heat-stripping techniques	▶ Easier, faster, more secure connections
▶ Utilizes Alcatel's proprietary Advanced Plasma and Vapor Deposition (APVD) process	▶ Ensures fiber with superior geometry and uniformity, as well as enhanced purity
▶ Utilizes Alcatel's unique fiber coating-AFC™	▶ Increased reliability and durability, resulting in lower maintenance and replacement costs
▶ Proprietary ColorLock™ process which makes the fiber color a component of the coating	▶ The fiber color is always consistent and distinguishable, ensuring increased ease-of-use and flexibility

KEY INDUSTRY LEADING MILESTONES

- ▶ **1993**- Introduced Alcatel's AFC™ coating process for superior aging performance
- ▶ **1994**- Introduced Alcatel's proprietary Advanced Plasma and Vapor Deposition (APVD) fiber production process to ensure the highest quality fiber
- ▶ **1996**- Developed and introduced ColorLock™, enhancing fiber identification and colored fiber reliability

Alcatel 6900 Singlemode Fiber

OPTICAL SPECIFICATIONS	
Attenuation (cabled)	
Attenuation @ 1310nm	≤ 0.35 dB/km
Attenuation @ 1550nm	≤ 0.25 dB/km
Attenuation at 1383nm	≤ 1.5 dB/km
Attenuation Uniformity (cabled)	
No point discontinuity greater than 0.1 dB at 1310nm and 1550nm.	
Wavelength vs. Attenuation	
Maximum attenuation change over the window.	
<u>Wavelength (nm)</u>	<u>Attenuation (dB/km)</u>
1285-1310	≤ 0.035
1310-1330	≤ 0.03
1525-1550	≤ 0.03
1575-1550	≤ 0.03
Attenuation with Bending	
100 turns, 60mm diameter @ 1550 & 1620nm:	≤ 0.05 dB
1 turn, 32mm diameter @ 1550 & 1620nm:	≤ 0.5 dB
Wavelength	
Cutoff Wavelength (cabled)	≤ 1260nm
Zero Dispersion Wavelength	1310±10nm
Dispersion Slope	
Zero Dispersion Slope	< 0.092 ps/nm ² *km
PMD (cabled)	
PMD Quadrature Average:	≤ 0.1ps/√km

DIMENSIONAL SPECIFICATIONS	
Mode Field Diameter @1310nm:	9.0±0.5µm
Mode Field Diameter @1550nm:	10.2±1.0µm
Fiber Outside Diameter:	125.0±1.0µm
Core/Cladding Offset:	≤ 0.6µm
Fiber Non-Circularity:	≤ 1.0%
Colored Coating Outside Diameter:	242±7µm
Colored Coating/Clad Concentricity Error:	≤ 12µm
Fiber Curl (radius):	> 4 meters

Alcatel's Singlemode Fiber is fully ITU G.652, IEC 60793-1 and Telcordia GR-20-CORE compliant.

Cable specifications apply to Alcatel manufactured cables and are tested or characterized in compliance to international standards.

Alcatel reserves the right to change specifications without prior notice.

MECHANICAL SPECIFICATIONS	
Proof Test of AFC™ ColorLock™ Coated	
The entire length is subjected to a tensile proof stress >100 kpsi (0.7 GN/m ²); 1% strain equivalent	
Tensile Strength	
Dynamic Tensile Strength (0.5 meter gauge length): Aged* & Unaged median ≥ 550 kpsi (3.8GN/m ²)	
Dynamic and Static Fatigue	
Dynamic Fatigue, Tensile:	N _d ≥ 20 unaged and aged*
Dynamic Fatigue, 2 Point Bend:	N _d ≥ 20 unaged and aged*
Static Fatigue:	N _s ≥ 20 aged at 85°C, 85% RH
Coating Strip Force	
Coating Strip Force:	2.0lbf (8.9N) max, 0.3 lbf (1.3N) min.
23°C, 0°C, and 45°C	
Aged: 30 days at 85°C and 85% relative humidity	
14 days water immersion at 23°C	
Wasp spray exposure (Telcordia)	
Aged: 30 days at 85°C water	No delimitation

ENVIRONMENTAL SPECIFICATIONS	
Induced Attenuation@1550nm	(dB/km)
Temperature Cycling Performance (-60°C to 85°C):	≤ 0.05
Temperature Humidity Cycling (-10°C to 85°C, 4-98%RH):	≤ 0.05
Water Immersion (23°C):	≤ 0.05
Heat Aging (85°C):	≤ 0.05

TYPICAL CHARACTERIZATION VALUES	
Nominal Zero Dispersion Wavelength:	1310nm
Nominal Zero Dispersion Slope:	0.086 ps/nm ² *km
Effective Group Index @ 1310nm:	1.4640
@ 1550nm:	1.4645
Backscatter Coefficient @ 1310nm:	-76.7 dB
Backscatter Coefficient @ 1550nm:	-81.7 dB
Typical Core Diameter:	8.8µm
Dynamic Tensile Strength (*Aged):	median 750 kpsi (5.26GN/m ²)
(0.5m gauge length)	
Dynamic Fatigue (*Aged):	N _d = 22
Static Fatigue:	N _s ≥ 25 aged @ 85°C, 85% RH
Dispersion @ 1285-1330nm:	≤ 2.7 ps/nm*km
Dispersion @ 1550nm	≤ 17 ps/nm*km

*Aged for 30 days at 85°C. 85% relative humidity

For additional information visit Alcatel online or call your nearest Optical Fiber Sales Representative

www.alcatel.com/opticalfiber

Brazil.....	+55 11 3068 9993
France	+33 1 55 51 51 51
France (HQ).....	+33 1 39 19 12 00
Germany.....	+49 2166 27 2164
India.....	+91 11 335 9650
Spain.....	+34 942 247 111
UK.....	+44 1633 413 600
North America.....	+1 828 459 9787
	800 879 9862



ARCHITECTS OF AN INTERNET WORLD

Rev 0, Jan. 02