

APÉNDICE A

Clorets NF con reproceso elaborada el 14 de agosto del 2003

T base	81.4 °C
T glucosa	52.9 °C

Etapa	Temp. goma	aw	aw (prom.)	s²
Mezclado	48°C	0.509	0.509	0.005
		0.514		
		0.505		
Pre-extruder	49°C	0.500	0.519	0.017
		0.529		
		0.529		
Extruder	47 °C	0.562	0.562	0.007
		0.555		
		0.569		
Laminado	43°C	0.406	0.423	0.034
		0.390		
		0.436		
		0.408		
		0.477		

Clorets NF sin reproceso elaborada el 23 de agosto del 2003

Temp. de la base	74.6 °C
Temp. Glucosa	50.8 °C

Etapa	Temp. goma	aw	aw (promedio)	s²
Mezclado	45.6 °C			
Pre-extruder	48.7°C	0.533	0.521	0.011
		0.513		
		0.516		
Extruder	43.5 °C	0.556	0.550	0.006
		0.55		
		0.545		
Laminado	39.3 °C	0.467	0.451	0.020
		0.428		
		0.457		